

**RIGA**[®]

FOOT

Product

Birch plywood (*Riga Ply*) overlaid with a phenol (dark brown, black, green) or an UV resistant (grey) film on both sides. The wear face has a special surface pattern (*WT*). The reverse face usually is smooth (*F*).

Application

Flooring, transport industry, storage and factory floors, storage shelves, loading platforms, pier surfaces, scaffoldings, playgrounds, and flight cases. In general surfaces where high wear resistance, anti-slip properties and good visual appearance are required.

Further processing

Plywood can be machined with wood working tools: cutting, drilling, milling, jointing in length, tongue and groove (*T&G*), half laps, profiled edges etc.

Advantages

Surface with high wear resistance, anti-slip properties, good visual appearance (decorative surface), weather- and water-proof, resists commonly used chemicals and easy-to-clean.

In addition, the product is environmentally friendly and hygienic.

Gluing classes

Plywood is glued with waterproof phenol formaldehyde resin adhesive. The weather and boiling water resistant bonding meets the requirements of the following standards:

EN 314 / 3rd class;

BS 1203 / H 4 (previously WBP);

DIN 68705 Part 3 / type BFU 100.

Formaldehyde emission


In accordance with the standard *EN 13986* the formaldehyde emission meets the *Class E1* requirements (test method *EN 717 Part 2*). Plywood glued with phenol-formaldehyde resins meets the *CARB Phase 2* and Japanese *4-Star Regulation's* requirements.

LATVIJAS FINIERIS**AKCIJU SABIEDRĪBA**

Bauskas 59, Rīga, LV-1004, Latvia
Phone +371 67620857, Fax +371 67820112
E-mail: info@finieris.lv
<http://www.finieris.com>

RIGA[®] FOOT


Surface pattern




The panels are overlaid with a phenol film and have a special pattern imprinted in hot pressing process.

Anti-slip Class in accordance with *DIN 51130 R 10*.

The abrasion resistance of *Riga Foot* and *Riga Foot Heavy* is fundamentally different.

 Foot surface pattern

Type of overlay	<i>Taber test</i> results, revolutions	<i>Rolling test</i> results, revolutions
 Foot <ul style="list-style-type: none"> ▶ Grey ▶ Dark brown ▶ Green 	At least 1 200 At least 600 At least 600	At least 10 000 At least 8 000 At least 8 000

Edge sealing

The panels' edges are sealed with an acrylic paint, to avoid absorption of moisture. The edge sealing paint and the panels' face colors match, but even other colors are available upon request.

Sizes

1220 mm x 2440 / 3050mm
 1250 mm x 2500 / 3000mm
 1500 mm x 2500 / 3000 mm
 1525 mm x 2440 / 3050 mm

Cut-to-size panels and machined panels available in accordance with the customers' requirements.

Thickness

6.5, 9, 12, 15, 18, 21, 24, 27, 30, 35 mm.

Tolerance

Dimensional and right angle tolerance meets the standard *EN 315* requirements.

Nominal thickness, mm	6.5	9	12	15	18	21	24	27	30	35
Number of plies	5	7	9	11	13	15	17	19	21	25
Average actual thickness, mm	6.4	9.2	12.0	14.9	17.7	20.5	23.4	26.5	29.4	35
Lower limit, mm	6.1	8.8	11.5	14.3	17.1	20.0	22.9	25.8	28.7	33.6
Upper limit, mm	6.9	9.5	12.5	15.3	18.1	20.9	23.7	26.8	29.9	35.4

Parameter	Tolerance
Length, width (mm)	
< 1000	± 1 mm
1000...2000	± 2 mm
> 2000	± 3 mm
Right angle	± 0.1 %
Edge straightness	± 0.1 %

Plywood is manufactured by *AS Latvijas Finieris* whose Quality Management System is certified to the requirements of *ISO 9001* by *Bureau Veritas Certification*.

