



RIGA

HPL

Product

Birch plywood (Riga Ply) overlaid with HPL (High Pressure Laminate) on one or both faces. On the reverse side balance paper can be applied.

Overlay

HPL is a decorative high-pressure laminate. HPL is made of layers of Kraft paper impregnated with phenol resins (the core) and decorative melamine impregnated paper (the surface layer), manufactured under high pressure and temperature.

Colours at customer's request.

Application

Furniture industry: kitchen and laboratory furniture components and worktops; furniture for shops.

Transport industry and construction: finishing works of walls and ceiling, surfaces where high wear resistance and appearance are required.

Gluing classes

Plywood is glued with waterproof phenol formaldehyde resin adhesive. The weather and boiling water resistant bonding meets the requirements of the following standards:

EN 314 / 3rd class;

BS 1203 / H 4 (previously WBP);

DIN 68705 Part 3 / type BFU 100.

HPL overlay is glued to the surface of plywood with high resistance melamine-urea-formaldehyde glue.

HPL bonding quality meets requirements of:

EN 12765/class C4;

DIN 68705 / AW 100;

BS 1204, BS 1203 / BR.

Formaldehyde emission

In accordance with the standard EN 13986 the formaldehyde emission meets the Class E1 requirements (test method EN 717 Part 2). Plywood glued with phenol-formaldehyde resins meets the CARB Phase 2 and Japanese 4-Star Regulation's requirements.

LATVIJAS FINIERIS

AKCIJU SABIEDRĪBA



Bauskas 59, Rīga, LV-1004, Latvia
Phone +371 67620857, Fax +371 67820112
E-mail: info@finieris.lv
<http://www.finieris.com>

RIGA[®] HPL

Sizes

1220 x 2400 / 3050 mm

1250 x 2500 / 3000 mm

Cut-to-size panels and machined panels available in accordance with the customers' requirements.

Thickness

Plywood (Riga Ply) nominal thickness is 6.5, 9, 12, 15, 18, 21, 24, 27 mm.

To Riga Ply thickness the following should be added:

2 x 0.6 mm (HPL thickness), if HPL is applied on both sides;

0.6 + 0.15 mm (balance paper thickness), if HPL is applied only on one side.

Tolerance

Dimensional and right angle tolerance meets the standard EN 315 requirements.

Nominal thickness, mm	6.5	9	12	15	18	21	24	27
Number of plies	5	7	9	11	13	15	17	19
Average actual thickness, mm	6.4	9.2	12.0	14.9	17.7	20.5	23.4	26.5
Lower limit, mm	6.1	8.8	11.5	14.3	17.1	20.0	22.9	25.8
Upper limit, mm	6.9	9.5	12.5	15.3	18.1	20.9	23.7	26.8

Parameter	Tolerance
Length, width (mm)	
< 1000	± 1 mm
1000...2000	± 2 mm
> 2000	± 3 mm
Right angle	± 0.1 %
Edge straightness	± 0.1 %

Plywood is manufactured by AS Latvijas Finieris whose Quality Management System is certified to the requirements of ISO 9001 by Bureau Veritas Certification.



The given information is for reference only and AS Latvijas Finieris reserves the rights to amend and supplement the specifications of manufactured products without a prior notice.